



Base Types

- Dense Graded Aggregate Base (4" & 6")
- Permeable Bituminous Treated Base (4") **Note: These are the only Sections with Edge Drains**
- Lean Concrete Base (6")
- Salvaged Base

Lane Width

- 12 ft Lane Width
- 14 ft Lane Width

PCCP Mix Type

- 550 Mix
- 900 Mix

Test Section	PCC PVMT Thickness (Inches)	PCC PVMT Width (Feet)	14 Day Flexural Strength (psi)	Base Type	Joint Orientation	Transverse Joint Spacing (Feet)	Type of Load Transfer Device
380259	10	24	*	8" SALVE	SKEWED	15	DOWELS
380260	11	38	*	CL 5 AGGR	SKEWED	15	DOWELS
380261	11	24	550	CL 5 AGGR	SKEWED	VARIABLE **	NONE
380262	11	28	550	LCB	SKEWED	VARIABLE	NONE
380263	11	24	550	PASB	SKEWED	VARIABLE	NONE
380264	11	38	*	PASB	SKEWED	15	NONE

Note: 380259 North Dakota DOT control test section.
 * Class AE as per NDDOT Specifications.
 ** Joint spacing varies from 12; 15; 13 and 14 ft.